

BULK DENSITY OF PULVERIZED MATERIALS IN FREELY POURED CONDITION^a

Material	Average Weight lbs./ft. ³	g/cm ³	Material	Average Weight lbs./ft. ³	g/cm ³	Material	Average Weight lbs./ft. ³	g/cm ³
Alumina	44	1.23	Fullers earth	30 to 40	0.48 to 1.04	Rubber, chopped	36	0.58
Aluminum, calcined	128	2.05	Garnet	168	2.69	Rubber, ground	20	0.32
Aluminum oxide	122	1.96	Glass beads	76	1.22	Phosphate rock	75 to 85	1.20 to 1.36
Aluminum shot	96	1.54	Glass, crushed	66	1.06	Salt, flake	61	0.98
Ammonium nitrate	48	0.77	Glass cullet	93	1.49	Salt, rock	66	1.06
Ammonium - sulfate	61	0.98	Granite, crushed	95 to 100	1.52 to 1.60	Salt, table	75	1.20
Bauxite ore	75 to 85	1.20 to 1.36	Gravel	90 to 100	1.44 to 1.60	Sand	90 to 100	1.44 to 1.60
Bentonite	50 to 65	0.80 to 1.04	Gypsum, calcined	58	0.93	Sand, silica	90 to 100	1.44 to 1.60
Bicarbonate of soda	57	0.91	Gypsum, crushed	90 to 100	1.44 to 1.60	Sawdust	18	0.29
Borax	50 to 61	0.80 to 0.98	Iron ore	120 to 150	1.92 to 2.40	Seacoal	42	0.67
Boric acid	58	0.93	Kaolin	160	2.56	Shale	100	1.60
Calcite	90	1.44 to 1.68	Kyanite	68	1.09	Shot, metal	230	3.69
Calcium carbide	75	1.20	Lime, ground	60	0.96	Silica, flour	27	0.43
Calcium carbonate	49	0.79	Lime, hydrated	25	0.40	Silica, gel	45	0.72
Calcium chloride	64	1.03	Limestone, crushed	85 to 100	1.36 to 1.60	Soapstone, pulverized	40	0.64
Calcium phosphate	57	0.91	Limestone, agricultural	70	1.12	Soda ash, light	25 to 35	0.40 to 0.56
Carbon black	24	0.33	Magnesite	106	1.70	Soda ash, heavy	55 to 65	0.88 to 1.04
Cellulose powder	16	0.26	Magnetite	155	2.49	Soda, bicarbonate	57	0.91
Cement, portland	90 to 100	1.44 to 1.60	Manganese ore	120 to 136	1.92 to 2.18	Sodium nitrate	78	1.25
Cement clinker	75 to 80	1.20 to 1.28	Marble, crushed	90 to 95	1.44 to 1.52	Sodium phosphate	43	0.69
Chrome ore	140	2.25	Metals, powdered			Sodium sulfate	96	1.54
Clay	30 to 75	0.48 to 1.20	Aluminum	80	1.28	Steel grit	228	3.66
Coal, anthracite	55	0.88	Copper	169	2.71	Stone, crushed	85 to 95	1.36 to 1.52
Coal, bituminous	50	0.88	Copper-lead	364	5.84	Sugar, granulated	5	0.80
Coke breeze	25 to 35	0.40	Iron	243	3.90	Sugar, powdered	37	0.59
Coke, petroleum	25 to 40	0.40 to 0.64	Nickel	263	4.22	Sulphur, crushed	50 to 65	0.80 to 1.04
Copper ore	100 to 150	1.60 to 2.40	Stainless steel	240	3.85	Talc, powder	34	0.55
Coquina shell	80	1.28	Tantalum	300	4.80	Talc, granular	44	0.71
Corn starch	40	0.64	Mica	42	0.67	Traprock, crushed	105 to 110	1.68 to 1.76
Diatomaceous earth	31	0.50	Ore, sintered	144	1.83	Triple superphosphate,		
Dicalcium phosphate	64	1.03	Oyster shells, ground	29	0.47	granular	64	1.03
Dolomite, crushed	90 to 100	1.44 to 1.60	Perlite ore	65 to 75	1.04 to 1.20	Tungsten carbide	550	8.82
Feldspar, crushed	65 to 84	1.04 to 1.35	Plaster, calcined	64	1.03	Urea prills	43	0.69
Ferrophosphorous	196	3.14	Polyethylene pellets	36	0.58	Vermiculite ore	80	1.28
Fire clay	80	1.28	Polyethylene powder	18	0.29	Wood chips	13	0.21
Flour, wheat	24	0.38	Poly vinyl chloride	30	0.48	Zinc dust	144	2.31
Flour, maize	37	0.59	Potash	77	1.23	Zirconium oxide	200	3.22
Fluorspar	90 to 120	1.44 to 1.92	Potassium carbonate	79	1.27	Zirconium sand	162	2.60
Fly ash	49	0.79	Pumice	40	0.64			

^a - Where a single figure is given, it represents an actual weight of a typical average sample of the material recorded by a research laboratory; therefore, the figure can be expected to vary from sample to sample of the same material.

Table 5